



AB MARTIN ROOFING SUPPLY

PRODUCT TYPE	PRODUCT COLOR	VALSPAR ITEM CODE	SUBSTRATE	INITIAL SOLAR REFLECTANCE	INITIAL EMISSIVITY	SOLAR REFLECTIVE INDEX (SRI)
WEATHERXL	ASH GRAY	WXA0092L	GALVALUME	.46	.86	52
WEATHERXL	ASH GRAY	WXA0092L	HDG	.41	.86	45
WEATHERXL	TAN	WXD0049L	GALVALUME	.45	.86	50
WEATHERXL	TAN	WXD0049L	HDG	.40	.86	43
WEATHERXL	FOREST GREEN	WXG0020L	GALVALUME	.28	.86	27
WEATHERXL	FOREST GREEN	WXG0020L	HDG	.20	.86	17
WEATHERXL	EVERGREEN	WXG0032L	GALVALUME	.35	.86	37
WEATHERXL	EVERGREEN	WXG0032L	HDG	.29	.86	29
WEATHERXL	SCARLETT RED	WXR0079	GALVALUME	.44	.86	49
WEATHERXL	SCARLETT RED	WXR0079	HDG	.34	.86	35
WEATHERXL	BRIGHT WHITE	WXW0053L	GALVALUME	.69	.85	83
WEATHERXL	BRIGHT WHITE	WXW0053L	HDG	.63	.85	75
WEATHERXL	SLATE BLUE	WXL0031L	GALVALUME	.39	.86	42
WEATHERXL	SLATE BLUE	WXL0031L	HDG	.33	.86	34
WEATHERXL	LIGHT STONE	WXD0038L	GALVALUME	.56	.86	65
WEATHERXL	LIGHT STONE	WXD0038L	HDG	.50	.86	57

Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371. SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Laboratory and Exposure site are ISO 17025 Accredited, Laboratory is also EPA Accredited. Panels are unwashed.

The VALSPAR CORPORATION certifies these tests to be true and accurate and performed by our laboratory.



AB MARTIN ROOFING SUPPLY

PRODUCT TYPE	PRODUCT COLOR	VALSPAR WEATHERXL ITEM CODE	SUBSTRATE	INITIAL SOLAR REFLECTANCE	INITIAL EMISSIVITY	SOLAR REFLECTIVE INDEX (SRI)
WEATHERXL	BARN RED	WXR0087L	GALVALUME	.37	.85	39
WEATHERXL	BARN RED	WXR0087L	HDG	.31	.85	31
WEATHERXL	BRONZE	WXB1043L	GALVALUME	.29	.87	29
WEATHERXL	BRONZE	WXB1043L	HDG	.21	.87	19
WEATHERXL	BEIGE	WXD0093L	GALVALUME	.66	.86	79
WEATHERXL	BEIGE	WXD0093L	HDG	.59	.86	70
WEATHERXL	CLAY	WXD0095L	GALVALUME	.49	.86	56
WEATHERXL	CLAY	WXD0095L	HDG	.43	.86	48
WEATHERXL	BLACK	WXA0107L	GALVALUME	.31	.84	31
WEATHERXL	BLACK	WXA0107L	HDG	.17	.84	12
WEATHERXL	EARTH BROWN	WXB1015L	GALVALUME	.34	.86	35
WEATHERXL	EARTH BROWN	WXB1015L	HDG	.28	.86	27
WEATHERXL	BURGUNDY	WXR0078L	GALVALUME	.28	.86	27
WEATHERXL	BURGUNDY	WXR0078L	HDG	.21	.86	18
WEATHERXL	CHARCOAL	WXA0098L	GALVALUME	.37	.86	39
WEATHERXL	CHARCOAL	WXA0098L	HDG	.29	.86	29
WEATHERXL	PEWTER GRAY	WXA0104L	GALVALUME	.46	.87	52
WEATHERXL	PEWTER GRAY	WXA0104L	HDG	.39	.87	43

Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371. SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Laboratory and Exposure site are ISO 17025 Accredited, Laboratory is also EPA Accredited. Panels are unwashed.

The VALSPAR CORPORATION certifies these tests to be true and accurate and performed by our laboratory.



AB MARTIN ROOFING SUPPLY

PRODUCT TYPE	PRODUCT COLOR	VALSPAR WEATHERXL ITEM CODE	SUBSTRATE	INITIAL SOLAR REFLECTANCE	INITIAL EMISSIVITY	SOLAR REFLECTIVE INDEX (SRI)
WEATHERXL	AVACADO GREEN	WXG0067L	GALVALUME	.31	.85	31
WEATHERXL	AVACADO GREEN	WXG0067L	HDG	.27	.85	26
WEATHERXL	GOLD	WXY0341L	GALVALUME	.53	.87	62
WEATHERXL	GOLD	WXY0341L	HDG	.45	.87	51
WEATHERXL	GALLERY BLUE	WXL0026L	GALVALUME	.25	.85	24
WEATHERXL	GALLERY BLUE	WXL0026L	HDG	.22	.85	19
WEATHERXL	RUSTIC TRED	WXR077L	GALVALUME	.36	.86	38
WEATHERXL	RUSTIC RED	WXR0077L	HDG	.32	.86	33
WEATHERXL	BONE WHITE	WXW0100L	GALVALUME	.61	.86	72
WEATHERXL	BONE WHITE	WXW0100L	HDG	.55	.87	64
WEATHERXL	DARK BLUE	WXL0052L	GALVALUME	.17	.86	13
WEATHERXL	DARK BLUE	WXL0052L	HDG	.15	.86	11
WEATHERXL	PATINA GREEN	WXG0066L	GALVALUME	.40	.83	42
WEATHERXL	PATINA GREEN	WXG0066L	HDG	.38	.83	40
WEATHERXL	COLONIAL RED	WXR0142L	GALVALUME	.33	.87	35
WEATHERXL	COLONIAL RED	WXR0142L	HDG	.28	.86	27

Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371. SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Laboratory and Exposure site are ISO 17025 Accredited, Laboratory is also EPA Accredited. Panels are unwashed.

The VALSPAR CORPORATION certifies these tests to be true and accurate and performed by our laboratory.